

PCT

BEST AVAILABLE COPY
WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01M 8/14, 4/86		A1	(11) International Publication Number: WO 00/08702 (43) International Publication Date: 17 February 2000 (17.02.00)
(21) International Application Number: PCT/NL99/00501 (22) International Filing Date: 6 August 1999 (06.08.99) (30) Priority Data: 1009815 6 August 1998 (06.08.98) NL (71) Applicant (for all designated States except US): STICHTING ENERGIEONDERZOEK CENTRUM NEDERLAND [NL/NL]; Westerduinweg 3, NL-1755 LE Petten (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): MAKKUS, Robert, Christiaan [NL/NL]; Karekietstraat 8, NL-1826 JM Alkmaar (NL). SITTERS, Eric, Franciscus [NL/NL]; Drevelstraat 39, NL-1825 KL Alkmaar (NL). (74) Agent: DE BRUIJN, Leendert, C.; Nederlandsch Octrooibureau, Scheveningseweg 82, P.O. Box 29720, NL-2502 LS The Hague (NL).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> <i>In English translation (filed in Dutch).</i>	
(54) Title: METHOD FOR THE PRODUCTION OF AN MCFC ELECTROCHEMICAL CELL			
(57) Abstract <p>Method for the production of an electrochemical cell consisting of an anode and cathode separated by an electrolyte-containing matrix. With this method electrolyte is melted into the green cathode at elevated temperature to improve the stability thereof and thereafter the cell is combined and then heated. With this method the cathode can consist of two or more layers or can have been produced, starting from a mixture, by casting a tape which consists of a mixture of lithium cobaltite and carbonate. Melting-in of the electrolyte material takes place by heating in a furnace.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Method for the production of an MCFC electrochemical cell

The present invention relates to a method according to the precharacterising clause of Claim 1.

5 A method of this type is disclosed in EP 0 509 424 A-2. A cathode consisting of two layers is described in PCT application PCT/NL 95/00306 in the name of the Applicant (European Application no. 95930058.3). A cathode of this type is produced by placing said two layers on top of one another in the green state, for example by tape casting, and then
10 combining the green cathode together with the other green components of the cell and heating. With this arrangements a matrix plate is present between the anode and cathode and the electrolyte material is introduced into the matrix plate in the cell in some way or other during start-up.

Although an electrochemical cell of this type has an excellent performance, it has been found that problems arise during the start-up phase. In particular, during initial heating the
15 strength of the cathode is inadequate to provide for continuous contact pressure against the matrix plate. This is caused, inter alia, by the reduction in thickness of the cathode during this start-up. This reduction in thickness can be, for example, 25 %.

The production of a green tape consisting of a mixture of cathode and electrolyte constituents is described in European Application 0 509 424. The green tape is combined
20 with at least one other green tape, which comprises the anode, and heated. Melting of carbonate into the electrode will take place in the first part of the heating curve and at higher temperatures sintering takes place.

It has been found that this type of method of combination also offers inadequate guarantees for strength in respect of the tape in which the cathode is incorporated to provide
25 for continuous contact with the matrix plate.

The aim of the present invention is to prevent the disadvantages described above.

This aim is achieved with a method as described above by means of the characterising features in Claim 1.

In contrast to EP 0 509 424, in the case of the invention the electrolyte is introduced
30 into the green, i.e. unsintered, cathode material in a separate step. Such introduction can take place at elevated temperature, but this temperature is lower than the temperature at which sintering takes place. A value of 500°C for melting-in and a value of 950-1050°C for sintering may be mentioned by way of example. A sintered structure containing pores is not

produced during the first-mentioned treatment. Combination with other (green) components of the cell takes place only thereafter, preferably only after cooling of the cathode provided with electrolyte to room temperature.

The method described above imparts adequate strength to the cathode to enable the latter to be placed against the matrix with adequate contact force during start-up. The reduction in thickness that is detected during start-up is appreciably restricted, as will be illustrated in more detail below with the aid of the examples.

The green cathode described above can be any cathode known in the prior art.

According to a first variant, the cathode comprises a tape in which the carbonate (electrolyte) material has been incorporated. This tape is preferably produced by using a mixture of lithium cobaltite and carbonate particles as the starting material. This is in contrast to what is described in PCT application 94/18713, in which the starting material is cobalt particles which oxidise in the cell. Structural modifications, which have consequences for the pore size distribution, are found to take place as a result of this oxidation. This is avoided by using lithium cobaltite powder as the starting material.

According to a further advantageous embodiment, the cathode consists of a structure of at least two layers. These layers are placed on top of one another in the green state, after which melting-in of electrolyte takes place. These layers can be a layer based on lithium cobaltite and a layer containing (semi-)noble metal particles. An example thereof is a layer containing nickel particles and the last-mentioned layer will be directed towards the separator plate or current collector during use and is primarily of importance because of the conductance, whilst the layer based on lithium cobaltite is designed more in order to allow the cathodic reaction to proceed in an optimum manner.

In the latter case the method is carried out under oxidising conditions. If a tape in which the nickel layer is already present is used as the starting material, the method is carried out under a reducing atmosphere and during this procedure the electrolyte can optionally be applied as a tape.

Another possibility is that an electrolyte tape is applied to the cathode. The electrolyte tape consists of electrolyte and the electrolyte and binder are melted into the green cathode under elevated temperature. This process can take place under reducing conditions. In this case also the product thus obtained is not sintered. Sintering takes place later, either in a separate step or after combining the assembly in the electrochemical cell with anode and other components. In this context it is possible to allow the (semi-)noble metal-containing

tape already to form part of the cathode before the electrolyte is introduced or to apply said (semi-)noble metal-containing tape only after the electrolyte has been introduced into the layer based on lithium cobaltite.

The invention will be explained in more detail below with the aid of two examples.

5

Example 1

A green lithium cobaltite tape is produced by mixing together LiCoO_2 powder, ethanol and Tween (surface-active agent). Methylcellulose (with binder), demineralised water and TBP (solvent) are then added with continuous stirring. A tape is then cast in the manner described in PCT application PCT/NL95/00306. The tape is then dried.

10 An electrolyte tape consisting of a mixture of Li_2CoO_3 , Na_2CO_3 and K_2CO_3 is then placed by the tape casting technique on top of said green LiCoO_2 tape. The whole is heated in an oxidising gas atmosphere to 500°C just above the melting point of the electrolyte and remains at this temperature for approximately 30 minutes. During this operation the liquid
15 electrolyte transfers from the electrolyte tape into the green LiCoO_2 tape. Cooling to room temperature then takes place. It has been found that the solidified electrolyte now present in the cathode tape increases the strength of the latter and protects the lithium cobaltite during start-up in an MCFC fuel cell. Before or during the operation to incorporate the lithium
20 cobaltite cathode, containing melted-in electrolyte, thus obtained in an MCFC, a green nickel layer with a thickness of approximately $50\text{ }\mu\text{m}$ is applied to that side which subsequently comes into contact with the current collector. Good electrical contact between current collector and cathode is ensured by this means. A 3 cm^2 specimen was then subjected to a
25 start-up operation, this start-up taking place under both dry and wet nitrogen gas. In Fig. 1 the reduction in thickness of a cathode in the start-up phase is plotted as a function of the temperature, both for cathodes produced according to the prior art in combination with a separate supply of electrolyte and for cathodes according to the invention.

In this figure cathodes according to the prior art are indicated by a and b and a indicates start-up under dry conditions in nitrogen and b start-up under wet conditions. These results were obtained with the cell structure according to PCT application PCT/NL 95/00306. The
30 total reduction in thickness was at least 22 % of the initial thickness.

Two cathodes according to the invention are indicated by c and d, c indicating dry nitrogen and d wet nitrogen. Here again start-up took place under a nitrogen atmosphere and it can be seen that a reduction in thickness of at most 5 % takes place during start-up.

Consequently, it is possible to guarantee continuous contact between cathode and other parts of the electrochemical cell during the warm-up phase. No cracking was found, whilst if the fuel gas and oxygen are then supplied and the cell is taken into operation, the performance does not differ from the performance of a fuel cell as described in PCT application PCT/NL 95/00306. The various aspects are illustrated with the aid of Fig. 2, where a simulation of the fuel cell with a surface area of 3 cm^2 obtained in this way was carried out. For this purpose use was made of so-called "simulated system conditions". The values recorded do not differ substantially from those recorded for the cell in the PCT application described above.

It has been found that despite the better yield the cathodes produced in this way have to be supported during transport because of the brittleness thereof. Example 2 below was carried out in order to prevent this problem.

Example 2

The starting material used in this example is a green double tape, that is to say a tape consisting of two layers, in this case a layer of lithium cobaltite and a layer of nickel particles. The LiCoO_2 tape is obtained in the manner described above.

A nickel suspension is then cast on top of this using the tape casting technique. The nickel suspension is obtained by mixing nickel powder, methylcellulose, Tween, TBP and ethanol. After some time demineralised water is added and the mixture is stirred for half an hour.

After a green double tape has been obtained in this way, an electrolyte tape consisting of a mixture of Li_2CO_3 , Na_2CO_3 and K_2CO_3 is applied thereto. The electrolyte tape is placed on the lithium cobaltite part of the double tape. Melting-in of the electrolyte then takes place, that is to say electrolyte moves from the electrolyte tape to the LiCoO_2 layer as a result of heating under a reducing gas atmosphere to just above the melting point of the electrolyte 500°C . Heating takes place for 30 minutes. Ultimately the electrolyte penetrates not only into the LiCoO_2 layer but also into the nickel layer.

Cooling to room temperature then takes place. The electrolyte solidified in the cathode imparts strength to the cathode and protects the LiCoO_2 against reduction during start-up in the fuel cell. Because the green LiCoO_2/Ni tape is placed with the nickel side against a current collector when applying the electrolyte tape, said current collector can give the package that is thus obtained strength during subsequent transport and contact between the nickel layer and the current collector is optimised.

BEST AVAILABLE COPY

WO 00/08702

PCT/NL99/00501

5

It has been found that an MCFC cell obtained with the aid of this method has the same good characteristics as the MCFC cell described on the basis of Example 1.

From these two examples and the other part of the description it will be clear to those skilled in the art that numerous variations are possible without going beyond the scope of the invention as described in the appended claims.


5

Claims

1. Method for the production of an MCFC electrochemical cell, comprising the provision of an anode and green cathode combined as an assembly and separated by a matrix
5 plate with electrolyte, based on carbonate, as well as a separator plate, the electrolyte being introduced into the green cathode and the part thus obtained being combined with the anode and heated, characterised in that the introduction of electrolyte into the cathode comprises melting-in at elevated temperature.
2. Method according to Claim 1, wherein, after melting-in at elevated temperature, the
10 part thus obtained is cooled to room temperature before combining with the other components of the cell.
3. Method according to one of the preceding claims, wherein a tape comprising a mixture of lithium cobaltite and carbonate is provided.
4. Method according to one of the preceding claims, wherein said cathode comprises at
15 least two layers, a layer based on LiCoO_2 and a layer containing (semi-)noble metal particles, wherein said layer containing (semi-)noble metal particles is directed towards said separator plate and the electrolyte is melted into said LiCoO_2 layer.
5. Method according to Claim 4, wherein the electrolyte is melted into the green layer based on LiCoO_2 , after which the green layer containing (semi-)noble metal particles is
20 applied thereon.
6. Method according to Claim 5, wherein the introduction of electrolyte is carried out under oxidising conditions.
7. Method according to Claim 4, wherein a green cathode consisting of at least two layers is provided, into which the electrolyte is introduced and wherein the layer containing
25 (semi-)noble metal is placed against the separator plate/current collector, after which the assembly is combined.
8. Method according to Claim 7, wherein the introduction of electrolyte takes place under a reducing atmosphere.
9. Method according to one of the preceding claims, wherein the electrolyte comprises
30 a mixture of carbonates containing at least Li_2CoO_3 .
10. Method according to one of the preceding claims, wherein said (semi-)noble metal-containing particles comprise nickel.


1/2

Fig-1



2/2

fig-2



BEST AVAILABLE COPY

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 H01M8/14 H01M4/86		Int. Application No PCT/NL 99/00501
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 H01M		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 509 424 A (INST GAS TECHNOLOGY) 21 October 1992 (1992-10-21) cited in the application column 4, line 27 - line 37 column 8, line 8 - line 26; example VI <div style="text-align: center;">-/-</div>	1,9
<div style="display: flex; justify-content: space-between;"> <input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex. </div>		
* Special categories of cited documents : <div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed </div> <div style="width: 45%;"> "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "G" document member of the same patent family </div> </div>		
Date of the actual completion of the international search <div style="text-align: center;">16 December 1999</div>		Date of mailing of the international search report <div style="text-align: center;">28/01/2000</div>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3018		Authorized officer <div style="text-align: center;">D'hondt, J</div>

Form PCT/ISA210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Int. Appl. No.
PCT/NL 99/00501

C. (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>CHEMICAL ABSTRACTS, vol. 109, no. 2, 11 July 1988 (1988-07-11) Columbus, Ohio, US; abstract no. 9417, NIIKURA JUNJI ET AL: "Electrodes for molten-carbonate fuel cells" XP002125957 abstract -& PATENT ABSTRACTS OF JAPAN vol. 12, no. 291 (E-644), 9 August 1988 (1988-08-09) & JP 63 066858 A (MATSUSHITA ELECTRIC IND CO), 25 March 1988 (1988-03-25) abstract</p>	1,9
A	<p>NIIKURA J ET AL: "FABRICATION AND PROPERTIES OF COMBINED ELECTRODE/ELECTROLYTE TAPE FOR MOLTEN CARBONATE FUEL CELLS" JOURNAL OF APPLIED ELECTROCHEMISTRY, vol. 20, no. 4, 1 July 1990 (1990-07-01), pages 606-610, XP000453540 page 606, right-hand column, paragraph 1 - paragraph 3 page 607, right-hand column, paragraph 3 page 608, left-hand column, paragraph 1</p>	1,9
A	<p>WO 96 08050 A (STICHTING ENERGIE ;SITTERS ERIC FRANCISCUS (NL); HEUVELN FREDERIK) 14 March 1996 (1996-03-14) cited in the application column 4, line 5 - line 25; claims 1,5</p>	4,7,10
A	<p>US 4 891 280 A (KAUN THOMAS D ET AL) 2 January 1990 (1990-01-02) column 3, line 47 - line 63; claim 1</p>	1
A	<p>PATENT ABSTRACTS OF JAPAN vol. 098, no. 008, 30 June 1998 (1998-06-30) & JP 10 074529 A (TOSHIBA CORP), 17 March 1998 (1998-03-17) abstract</p>	1
A	<p>PATENT ABSTRACTS OF JAPAN vol. 017, no. 214 (E-1357), 27 April 1993 (1993-04-27) & JP 04 351854 A (MITSUBISHI ELECTRIC CORP), 7 December 1992 (1992-12-07) abstract</p>	1
A	<p>US 5 468 573 A (BREGOLI LAWRENCE J ET AL) 21 November 1995 (1995-11-21) column 1, line 46 - line 58; claim 1</p>	
	-/-	

Form PCT/ISA210 (continuation of second sheet) (July 1992)

BEST AVAILABLE COPY

INTERNATIONAL SEARCH REPORT

Int. Patent Application No
PCT/NL 99/00501

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 240 786 A (MARIANOWSKI LEONARD G ET AL) 31 August 1993 (1993-08-31) column 5, line 50 - line 57	
A	EP 0 678 926 A (ANSALDO UN AZIENDA FINMECC) 25 October 1995 (1995-10-25) claim 1	
A	WO 94 18713 A (MOTOREN TURBINEN UNION ; JANTSCH UWE (DE); KOCH HERMANN (DE); ROHLA) 18 August 1994 (1994-08-18) cited in the application page 6, last paragraph - page 7, paragraph 1; claims 1,12; example 1	

1

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

page 3 of 3

BNSDOCID: <WO_____0008702A1_1_>

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/NL 99/00501

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0509424 A	21-10-1992	JP 5198307 A US 5453101 A	06-08-1993 26-09-1995
WO 9608050 A	14-03-1996	DE 69507166 D DE 69507166 T EP 0804812 A ES 2129221 T JP 2960548 B JP 9512950 T US 5885309 A	18-02-1999 12-08-1999 05-11-1997 01-06-1999 06-10-1999 22-12-1997 23-03-1999
US 4891280 A	02-01-1990	US 4939111 A	03-07-1990
JP 10074529 A	17-03-1998	NONE	
JP 04351854 A	07-12-1992	JP 2894377 B	24-05-1999
US 5468573 A	21-11-1995	EP 0689258 A JP 8045524 A	27-12-1995 16-02-1996
US 5240786 A	31-08-1993	AT 134459 T CA 2091331 A,C DE 69301574 D DE 69301574 T EP 0560731 A JP 2593036 B JP 6044989 A	15-03-1996 14-09-1993 28-03-1996 04-07-1996 15-09-1993 19-03-1997 18-02-1994
EP 0678926 A	25-10-1995	IT 1269334 B DE 69510402 D DE 69510402 T ES 2134997 T JP 7326366 A US 5688292 A	26-03-1997 29-07-1999 21-10-1999 16-10-1999 12-12-1995 18-11-1997
WO 9418713 A	18-08-1994	DE 4303136 C EP 0682816 A JP 2846738 B JP 8506212 T US 5582624 A	16-06-1994 22-11-1995 13-01-1999 02-07-1996 10-12-1996

Form PCT/ISA/210 (patent family annex) (July 1992)

BNSDOCID: <WO 0008702A1_1_>